



GE Bayer Silicones



Certifications COMPLIANCE REPORT

GE Bayer Silicones bv
Plasticslaan 1, PO Box 117
3720 BC Bunnik, The Netherlands
Tel. (31) 164.29.2291
Fax. (31) 164.29.2708

INVOICE NR. : NLDBASI739669
PO NUMBER : 11102000
SAP 3131

GRADE CRTV-0201FI BATCH PK531
G430

PROPERTY TESTED	VALUE	MIN	MAX
IN-PROCESS TESTING			
APPEARANCE	OK	OK	
FLOW	INCH 0.03		0.25
APPLICATION RATE	G/MIN 371	REPORT	REPORT
SPECIFIC GRAVITY	G/CM3 0.994	0.985	
FIANL TESTS UNCURED MAT. (F)			
TACK FREE TIME	MIN 30		60
FINAL TESTS CURED MAT. (F)			
SHORE A	25	13	
ELONGATION	% 418	REPORT	REPORT
TENSILE	MPA 1.79	REPORT	REPORT

S - SPC A - AVERAGE
F - FREQUENCY

GE BAYER SILICONES
CUSTOMER PROGRAMS QUALITY ASSURANCE

IF STORED AT
TEMPERATURES UP TO 27C

Anja Thieren

NOTES/COMMENTS:

The material identified above was made and tested according to GE Bayer Silicones Quality Procedures. The reported values are a transcript from respective test data stored electronically. No such data should be interpreted as a product specification. Supply is made subject to GE Bayer Silicones Standard Conditions of Sale. (see reverse side if enclosed).

GE Bayer Silicones liability hereunder is limited as set forth in the warranty printed on the reverse side of this form.